

RECEIVED
APR 21 2014
BY: _____

Compressive Strength Report

Concrete
ASTM C-39

Client: Talisman Construction Services
Address: PO Box 6189
Spokane, WA 99217

Set #: C-1

Project: Talisman 2014 Materials Testing
Project #: L14116
Contractor: _____
Sampled By: Client
Sample Location: Custom Mix
Sample Date: 3/12/14
Date Received: 3/13/14
Supplier: Client
Mix #: Custom Mix
Ticket #: _____

Specified Strength: _____ psi

Slump ("): _____ (ASTM C-143, AASHTO T-119) Unit Weight (pcf): _____ (ASTM C-138, AASHTO T-121)
Entrained Air (%): _____ (ASTM C-231, AASHTO T-152) Yield (%): _____ (ASTM C-138, AASHTO T-121)
Temperature: _____ ° (ASTM C-1064) Initial Cure Temperature Min: _____ Max: _____


Sample I.D.	Test Date	Age (days)	Capping Method	Fracture Type	Diameter (.01 inch)	Load (lbs.)	Area (.01 inch ²)	Strength (p.s.i.)	% of Spec.
C-14-1097	03/19/14	7	UB	3	4.01	77950	12.63	6170	
C-14-1098	04/09/14	28	UB	4	4.01	83215	12.63	6590	
C-14-1099	04/09/14	28	UB	3	4.01	81590	12.63	6460	

Remarks: _____

Report Copy To: _____

Report By: _____

Terri Ballard
Terri Ballard, CET
Laboratory Manager



CAPPING METHOD
UB - ASTM C1231 - Use of Unbonded Caps
S - ASTM C617 - Sulfur Capping



Flexural Strength Report

Concrete
ASTM C-78

Client: Talisman Construction Services
Address: PO Box 6189
Spokane, WA 99217

Set #: B-1

Project: Talisman 2014 Materials Testing
Project #: L14116
Contractor: _____
Sampled By: Client
Sample Location: _____
Sample Date: 3/12/14
Date Received: 3/13/14
Supplier: _____
Mix #: Custom Mix
Ticket #: _____
Specified Strength: _____ psi

Slump: _____" (ASTM C-143, AASHTO T-119)
Entrained Air: _____% (ASTM C-231, AASHTO T-152)
Temperature: _____° (ASTM C-1064)
Initial Cure Temperature Min: _____ Max: _____

Unit Weight (pcf): _____
(ASTM C-138, AASHTO T-121)

Sample I.D.	Test Date	Age (days)	Width (.05 inch)	Depth (.05 inch)	Load (lbs.)	Span (inch)	Strength (p.s.i.)	% of Spec.
14-1106	03/19/14	7	6.03	6.02	9615	18	790	
14-1107	04/09/14	28	6.03	6.02	10075	18	830	
14-1108	04/09/14	28	6.02	6.02	10370	18	855	

Remarks: _____

Report By: Terri Ballard
Terri Ballard, CET
Laboratory Manager

Report Copy To: _____